



Makwell Organics Pvt. Ltd.

A-506, Bhaveshwar Plaza, L.B.S. Marg, Ghatkopar (W), Mumbai - 400 086. INDIA.
Tel: 91+22+25004848 • Fax 91 22 25004800 • Email : sales@makwellgroup.com

www.makwellgroup.com

Epoxidized Soyabean Oil Specifications

Grades	Makplast SNS
Appearance	Pale Yellow Liquid
Specific Gravity	0.97 - 0.99
Moisture Content %	0.2 % Max.
Oxirane Oxygen %	6.7 +/- 0.2 %
Acid Value %	0.5 % Max.
Volatile Loss at 160° C. For 2 Hours	0.3 Max.
IODINE VALUE%	2.0 Max.